

P.S. ELECTRIC - EASYWEED™ ELECTRIC

SPECIFICATIONS

 Composition	 Average Thickness	 Carrier	 Certifications
PU	90 microns	Adhesive polyester	REACH compliant    

APPLICATION INSTRUCTIONS

| Laser friendly 

 Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	 Blade	 Pressure	 Speed	 Time	 Temperature	 Pressure	 Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	45°	60 gf	20 cm/sec	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	hot/cold

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier hot/cold

PRODUCT HIGHLIGHTS

- reduced thickness
- peralescent finish
- bright colors

 NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

 Washing	 Ironing	 Tumble dry	 Dry cleaning	 Storage Shelf Life	 Storage Temperature	 Storage Conditions	 Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

 This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

